

ITO Performance Confirmation

ITEM NO. 30P-T130 (New Configurations)

Construction : Protect Film
30Ω ITO / 0.188mm PET Film
+ (Laminating) OCA
0.130mm TAC Film / Anti-fog surface
Protect Film

ITO Electrical resistance : 30Ω ± 5Ω

Anti-Fog Performance : 60 seconds in the 50°C steam,
Cloudiness is not generated.
(Average duration is over 90 seconds)

Optical overview

Transmissivity : Upper 80%

Haze : < 1.0

An alien substance : Nothing the over 0.5mmφ aliens

A wound & a dirt : Nothing the over 0.05mm / Width x 10mm / length one' s

Others : Non-carl, Non-waving

Size Width x length : Max 520mm x 300mm over
Thickness : 0.368mm

ITO Sheet Construction

ITO Sheet 0.368mm

